

TECHNICAL DATA SHEET



IC-972 1K Acrylic Primer

Description

IC-972 1K Primer Surfacer features good filling performance which makes the surface flatter and smoother. At the same time, it can enhance the adhesion between the coatings to ensure that the subsequent topcoat can be firmly attached and not easily fall off. It has a fast-curing time and easy to sand.



Features

- Excellent filling properties
- Fast drying time, dry to sand in 40 minutes
- Easy to sand

Required Products

- IC-972 Primer Surfacer
- IC-944 Reducer

Compatible Surfaces

- Properly prepared gel coated fiberglass
- Properly prepared OEM finishes
- Properly prepared E-coat
- Properly prepared steel & aluminum
- Rigid Plastics
- Body Fillers
- Epoxy Primers
- Self-etch Primers

IC-972

1K Acrylic Primer

Preparation of Substrate

- Wash the area to be painted with soap and water, then clean with IC-800 degreaser.
- Sand the old finishes with 240-360 grit dry by hand or machine or 600-800 grit wet.
- Reclean with IC-800 degreaser. The use of a tack rag is recommended.



Mixing Ratio

Product	Vol	Weight
IC-972	100	100
IC-944	100	70

Note:

Please shake for 30 s before mixing, and mix well and strain before application.



Pot Life

Indefinite in a sealed cup



Spray Viscosity

16-20 s with DIN 4 cup at 25°C



Spray Guns

Type	Nozzle Size	Pressure	Spray Distance
HVLP Gravity-feed Spray Gun	1.5-1.7 mm	1.8-2.0 bar	15-20 cm
Compliant Gravity-feed Spray Gun	1.6-1.8 mm	3.0-4.0 bar	20-25 cm

IC-972 1K Acrylic Primer



Number Of Coats

2 coats



Film Thickness

30-40 μm per coat



Drying Times

	20°C	60°C
Flash off	5-10 min	-
Dry to sand	40-45 min	-



Product Specifications

Color: Grey

Shelf Life: 24 months at 25°C

Theoretical Coverage: 250-300 m^2/L at 1 μm thickness

Ready to use density: 1071 g/l

Weight of ready to use solids: 29.6 %



Sanding

After fully cured, it will be necessary to sand the primer with 400-800 grit abrasives.

IC-972

1K Acrylic Primer

HEALTH AND SAFETY



Please refer to Material Safety Data Sheets for full Health and Safety details and product can labels.

- Hardeners contain isocyanate and therefore particular safety precautions must be taken.
- Goggles must be worn when mixing and using to prevent accidental splashing into the eye. If contact occurs with eyes give prolonged irrigation with water and get medical attention immediately.
- Good ventilation and extraction must be provided in the working environment.
- Wear suitable protective equipment to prevent skin contact with this material.
- When spraying this product the operator (and persons in vicinity) must wear suitable air-fed breathing apparatus.
- Do not smoke whilst using this material.

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. The Information is given for information purposes only and we are not liable for its correctness, accuracy and completeness. The intellectual property in this document, including patents, trademarks and copyrights, is protected. All rights reserved. Published technical data and instructions are subject to change without prior notice. All rules set forth in this clause shall apply accordingly for any future changes and amendments. You can obtain the latest version of technical data sheet from our website at www.wonder-global.com or directly from your supplier.

Revised: September 2024